



**CASE CODE: 6270**

<b><u>PRODUCT DESCRIPTION</u></b>				
<b><u>Composition:</u></b>		100% Rayon + binder		
<b>Property</b>		<b>Berry Test Method</b>	<b>Comparable ASTM Method</b>	<b>Target</b>
Weight	(oz/yd <sup>2</sup> )	TM-7027	ASTM D3776	1,36
Thickness	(mil /1 ply)	TM-7015	ASTM D5729	16
Wet CD Tensile	(3 ply, lbs)	TM-7012	ASTM D5034	2
Absorbency Rate (sec)		TM7023	ASTM D1117	2,5
Absorbency Capacity (%)		TM-7023	ASTM D3786	1116

**NOTE:** The physical properties mentioned above represent typical values of nonwoven fabric.

**CONFIDENTIAL**

