



## TECHNICAL DATA SHEET

### Fortitude™ (FOR) Hand Film

Superior puncture and tear resistance, high cling, roll damage-resistant hand film

PROPERTY	UNITS	TEST		TYPICAL RESULT	
		UNITS	METHOD		
Thickness	mil			0.28 (7.1)	0.32 (8.1)
	(micron)				
Dart Impact Strength	g		D1709	45	45
Tensile Strength @ Break	MD	psi	D882	8,700	8,700
	TD			2,500	2,500
Elongation @ Break	MD	%	D882	100	125
	TD			600	650
Elmendorf Tear Strength	MD	g	D1922	100	130
	TD			300	325

**Berry Global**  
101 Oakley Street  
Evansville, IN 47710  
CS 1.866.787.3456  
[www.berryplastics.com](http://www.berryplastics.com)

The data presented above is for the product type described and is based on random tests that are not statistically valid. The values should only be used for reference and are not to be used for any type of specification. Berry Global does not monitor these values or manufacture to these values. Please be advised that values are known to change based on normal manufacturing variables such as production line, and lot to lot variations of raw materials. There is no guarantee expressed or implied regarding the use of this information or its suitability for a particular application.