



TECHNICAL DATA SHEET

XH™ Hand Film

Stiff film, high clarity, quiet and easy unwind

PROPERTY	UNITS	TEST METHOD	TYPICAL RESULT				
Thickness	mil (micron)		0.40 (10.2)	0.42 (10.7)	0.47 (11.9)	0.59 (15.0)	
Dart Impact Strength	g	D1709	35	40	45	60	
Tensile Strength @ Break	MD	psi	D882	4,500	4,500	4,500	4,500
	TD			2,175	2,175	2,175	2,175
Elongation @ Break	MD	%	D882	100	110	140	210
	TD			625	650	650	675
Elmendorf Tear Strength	MD	g	D1922	30	30	35	35
	TD			400	410	410	420

Berry Global

101 Oakley Street
 Evansville, IN 47710
 CS 1.866.787.3456
www.berryplastics.com

The data presented above is for the product type described and is based on random tests that are not statistically valid. The values should only be used for reference and are not to be used for any type of specification. Berry Global does not monitor these values or manufacture to these values. Please be advised that values are known to change based on normal manufacturing variables such as production line, and lot to lot variations of raw materials. There is no guarantee expressed or implied regarding the use of this information or its suitability for a particular application.