



TECHNICAL DATA SHEET

HWX™ Hand Film

Excellent puncture resistance, high stretch film, two-sided cling

| PROPERTY | UNITS | | TEST METHOD | TYPICAL RESULT | | | | | | | | | |
|--------------------------|----------|-----|-------------|----------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| | | | | | | | | | | | | | |
| Thickness | mil | | | 0.59 | 0.65 | 0.70 | 0.75 | 0.79 | 0.80 | 0.90 | 1.00 | 1.18 | 1.20 |
| | (micron) | | | (15.0) | (16.5) | (17.8) | (19.0) | (20.1) | (20.3) | (22.9) | (25.4) | (30.0) | (30.5) |
| Dart Impact Strength | g | | D1709 | 75 | 80 | 80 | 85 | 85 | 85 | 90 | 95 | 100 | 105 |
| Tensile Strength @ Break | MD | psi | D882 | 3,700 | 3,700 | 3,700 | 3,700 | 3,700 | 3,700 | 3,700 | 3,700 | 3,700 | 3,700 |
| | TD | | | 3,300 | 3,300 | 3,300 | 3,300 | 3,300 | 3,300 | 3,300 | 3,300 | 3,300 | 3,300 |
| Elongation @ Break | MD | % | D882 | 450 | 460 | 470 | 490 | 500 | 500 | 520 | 550 | 590 | 600 |
| | TD | | | 700 | 700 | 710 | 710 | 710 | 710 | 720 | 730 | 750 | 750 |
| Elmendorf Tear Strength | MD | g | D1922 | 65 | 70 | 75 | 80 | 80 | 80 | 90 | 100 | 120 | 120 |
| | TD | | | 460 | 480 | 490 | 510 | 520 | 520 | 550 | 580 | 640 | 640 |

Berry Global

101 Oakley Street
 Evansville, IN 47710
 CS 1.866.787.3456
www.berryplastics.com

The data presented above is for the product type described and is based on random tests that are not statistically valid. The values should only be used for reference and are not to be used for any type of specification. Berry Global does not monitor these values or manufacture to these values. Please be advised that values are known to change based on normal manufacturing variables such as production line, and lot to lot variations of raw materials. There is no guarantee expressed or implied regarding the use of this information or its suitability for a particular application.