



Case Good: 6116

| <u>PRODUCT DESCRIPTION</u> | | | | |
|-----------------------------------|--------|----------------------------------|-----------------------------------|---------------|
| <u>Composition:</u> | | 80% Rayon 20% Polyester + binder | | |
| Property | | Berry Test Method | Comparable ASTM Method | Target |
| Weight | osy | TM-7027 | ASTM D3776 | 2,23 |
| Thickness | (in) | TM-7015 | ASTM D5729 | 0,022 |
| Wet MD Tensile | (lbs.) | TM-7012 | ASTM D5034 | 20,0 |
| Wet CD Tensile | (lbs.) | TM-7012 | ASTM D5034 | 11,4 |
| Absorbency Time | (sec) | TM-7023 | ASTM D5802 | 1,4 |
| Absorbency Capacity | (%) | TM-7023 | ASTM D5802 | 1000 |

NOTE: The physical properties mentioned above represent typical values of nonwoven fabric.

CONFIDENTIAL