



MAXWRAP

Technical Data Sheet

Data points have been determined using the ESTL Test method certified under ISO 17025: General requirements for the competence of testing and calibration laboratories.

MAXWRAP		FILM THICKNESS		80 GAUGE (20.3 MICRON)
FILM PROPERTIES	UNIT	NOMINAL VALUE	TOLERANCE	
Ultimate @ Break	%	350	+/- 10%	
Ultimate force @ Break	Lbf	42	+/- 10%	
Load containment @ 300s	Lbf	5.3	+/- 10%	
Elmendorf tear strength force	Lbf	21	+/- 10%	
Time to break @ tear	Sec	43	+/- 10%	
Drop time @ tear	Sec	11	+/- 10%	
Puncture force	Lbf	9	+/- 10%	
Displacement @ puncture	Inch	3.7	+/- 10%	
Peel cling force @ 50 %	Lbf	0.13	+/- 10%	

NOTE: The data presented above are nominal values for the product type described and must not be construed as specifications. Therefore, no guaranty expressed or implied.