




# POLYAIR

## TECHNICAL PRODUCT SPECIFICATION

Revision No		Customer	<b>General Specification</b>
Issue Date:	13-Jan-2023	Description	<b>3/16" DURABUBBLE LITE 4'X750'</b>
Manufactured	<b>Toronto ON</b>	SLIT12	
Part Number	VLS <b>VLS48S12</b>		

PROPERTY	RESULT	U o M
NOMINAL CELL HEIGHT	3/16	inches
MATERIAL TYPE	LLDPE/LDPE blend	
DEFLATION	< 5	%
MINIMUM USAGE TEMPERATURE	-50 (°C)	-58 (°F)
MAXIMUM USAGE TEMPERATURE	80 (°C)	176 (°F)
MELTING POINT	137 (°C)	275 (°F)
RESISTANCE TO REDUCED PRESSURE	< 10	%
RECYCLED CONTENT	up to 20	%
SHELF LIFE	12	months

FINISHED PRODUCT			
	Min	Target	Max
Total Roll Width (inch)	47.75	<b>48</b>	48.25
Roll Length (feet)	750	<b>750</b>	772
Weight (Incl. Core, lbs)	26.57	<b>29.60</b>	32.65
Slit (inch)	11.75	12	12.25



PACKAGING			
Quantity	1	Roll / Bag	4 slits

Durabubble is made from a blend of low density polyethylene and linear low density polyethylene. Store drop off recyclable. May not be recyclable in your area.



The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, POLYAIR disclaims responsibility for results of use of this information. POLYAIR makes no warranties, either express or implied, concerning our materials, including any statements or suggestions as being inducements. All users should rely on their own test in determining suitability

This product data sheet is effective from 13-Jan-2023 and supersedes all previously published data.

POLYAIR (Division of Intertape Polymer Group)  
 Quality Assurance  
 330 HUMBERLINE DRIVE, TORONTO, ON M9W 1R5  
 TEL: 416-679-6600; FAX: 416-679-6610