



<b>ADW</b>									
<b>Property</b>	<b>Test Method Reference</b>	<b>Values</b>							
<i>Gauge, microns</i>		<b>13.0</b>	<b>14.5</b>	<b>16.5</b>	<b>17.8</b>	<b>19.0</b>	<b>20.3</b>	<b>22.9</b>	<b>25.4</b>
<b>Gauge, mil</b>	<b>ASTM D-374</b>	<b>0.51</b>	<b>0.57</b>	<b>0.65</b>	<b>0.70</b>	<b>0.75</b>	<b>0.80</b>	<b>0.90</b>	<b>1.00</b>
<b>Ult Tensile MD, psi</b>	<b>ASTM D-882</b>	5800	5800	5800	5800	5800	5800	5800	5800
<b>Ult Tensile TD, psi</b>	<b>ASTM D-882</b>	3200	3200	3200	3200	3200	3200	3200	3200
<b>Tens Yield MD, psi</b>	<b>ASTM D-882</b>	1900	1900	1900	1900	1900	1900	1900	1900
<b>Tens Yield TD, psi</b>	<b>ASTM D-882</b>	1600	1600	1600	1600	1600	1600	1600	1600
<b>Ult Elong MD, %</b>	<b>ASTM D-882</b>	300	300	300	300	340	380	440	540
<b>Ult Elong TD, %</b>	<b>ASTM D-882</b>	600	600	600	600	600	600	600	600
<b>1% Modulus MD, psi</b>	<b>ASTM D-882</b>	30000	30000	30000	30000	30000	30000	30000	30000
<b>1% Modulus TD, psi</b>	<b>ASTM D-882</b>	35000	35000	35000	35000	35000	35000	35000	35000
<b>Tear MD, g</b>	<b>ASTM D-1922</b>	70	90	100	110	120	140	160	190
<b>Tear TD, g</b>	<b>ASTM D-1922</b>	400	450	500	520	550	580	640	700
<b>Puncture, lbs</b>	<b>Internal</b>	7.9	9.3	10.7	11.0	11.2	11.5	12.0	12.5
<b>Dart Impact F50, g</b>	<b>ASTM D-1709A</b>	60	70	80	90	95	100	110	120

NOTE: The data presented above is for the product type described and is based on random tests that are not statistically valid. The values should only be used for reference and are not to be used for any type of specification. Berry Global does not monitor these values or manufacture to these values. Please be advised that values are known to change based on normal manufacturing variables such as production line, and lot to lot variations of raw materials. There is no guaranty expressed or implied regarding the use of this information or its suitability for a particular application.