



Technical Data Sheet

Data points have been determined using the ESTL Test method certified under ISO 17025: General requirements for the competence of testing and calibration laboratories.

Axis Loop	Film Thickness		67 Gauge 17.02 Micron
FILM PROPERTIES	UNIT	NOMINAL UNIT	TOLERANCE
Ultimate @ Break	%	330	+/- 10%
Ultimate Force @ Break	Lbf	35	+/- 10%
Load Containment @ 300s	Lbf	3.7	+/- 10%
Elmendorf Tear Strength Force	Lbf	26	+/- 10%
Time to Break @ Tear	Sec	19	+/- 10%
Drop Time @ Tear	Sec	2.6	+/- 10%
Puncture Force	Lbf	4.4	+/- 10%
Displacement @ Puncture	Inch	2.4	+/- 10%
Peel Cling Force @ 300%	Lbf	0.4	+/- 10%

NOTE: The data presented above are nominal values of the product type described and must not be constructed as specifications. Therefore, no guarantee expressed or implied.

