



Technical Data Sheet

Data points have been determined using the ESTL Test method certified under ISO 17025: *General requirements for the competence of testing and calibration laboratories.*

FILM PROPERTIES	Film Thickness		30 Gauge 7.62 Micron
	UNIT	NOMINAL UNIT	TOLERANCE
Ultimate @ Break	%	90	+/-10%
Ultimate Force @ Break	Lbf	34	+/-10%
Load Containment @ 300s	Lbf	4	+/-10%
Elmendorf Tear Strength Force	Lbf	16	+/-10%
Time to Break @ Tear	Sec	8	+/-10%
Drop Time @ Tear	Sec	1.5	+/-10%
Puncture Force	Lbf	4	+/-10%
Displacement @ Puncture	Inch	2.6	+/-10%
Peel Cling Force @ 300%	Lbf	0.3	+/-10%

NOTE: The data presented above are nominal values of the product type described and must not be constructed as specifications. Therefore, no guarantee expressed or implied.

